



1773

**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

Applicant(s): Yamanaka et al.

Examiner: Kruer, K.

Serial No.: 08/855,905

Group: Art Unit 1773

Filed: May 14, 1997

Docket: 443-17

For: SYNTHETIC PAPER MADE  
OF STRETCHED  
POLYPROPYLENE FILM

Date: November 22, 2002

RECEIVED  
NOV 29 2002  
TC 1700

#32  
LW  
12302


Assistant Commissioner for Patents  
Washington, D.C. 20231

**LETTER**

Responsive to the Notice of Non-Complaint Amendment mailed October 22, 2002 by the Patent and Trademark Office in the above-identified application, it is respectfully pointed out that a marked-up version of the amended claims was submitted with the amendment filed August 5, 2002.

In any event, a potentially clearer marked-up version of the amended claims is enclosed herewith.

Respectfully submitted,  
DILWORTH & BARRESE LLP.


  
George M. Kaplan  
Reg. No. 28,375  
Attorney for Applicant(s)

DILWORTH & BARRESE LLP.  
333 Earl Ovington Blvd.  
Uniondale, NY 11553  
(516) 228-8484 Telephone  
(516) 228-8516 Facsimile

**CERTIFICATE OF MAILING 37 C.F.R. § 1.8**

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope, addressed to the Assistant Commissioner for Patents, Washington, D.C. 2023.

Date: November 22, 2002

  
George M. Kaplan

1. A synthetic paper which comprises a film obtained by oxidizing the surface of a film obtained by stretching a resin film comprising as the base material a resin composition comprising

100 parts by weight of resin components and from 10 to 250 parts by weight of component E: fine inorganic particles;

said resin components comprising, based on the total weight of the resin components;

55-90 wt% of component A: a polypropylene resin, [55-90 wt%]

5-40 wt% of component B: a polyetheresteramide containing aromatic rings which is derived from

component b1: a polyamide having a number-average molecular weight of from 200 to 5,000 and containing a carboxyl group at each end, and

component b2: an [alkaline] alkylene oxide adduct of bisphenol having a number-average molecular weight of from 300 to 5,000, [5-40 wt%]

3-20 wt% of component C: a polyamide resin, [3-20 wt%] and

1-20 wt% of component D: at least one modified low-molecular weight polypropylene selected from the group consisting of

[following components d1 to d3]

[1-20 wt %]

component d1: an acid-modified low-molecular weight polypropylene having a number-average molecular weight of from 800 to 25,000 and an acid value of from 5 to 150,

component d2: a hydroxy-modified low-molecular weight polypropylene having a number-average molecular weight of from 800 to 25,000 and a hydroxyl value of from 5 to 150, and

component d3: an ester-modified low-molecular weight polypropylene obtained by partly or wholly esterifying component d1 with a polyoxyalkylene compound and having a number-average molecular weight of from 1,000 to 28,000; [.]

[the total amount of all resin components being 100 wt%;  
and  
from 10 to 250 parts by weight of

component E: fine inorganic particles,]

said stretching being conducted at a temperature lower than the melting point of the polypropylene resin as component A, said stretching and oxidation of said stretched film generating ultrafine cracks on a surface of said stretched film through which component B as permanent antistatic agent appears and possessing gloss of 60% or below and opaqueness of 83% or above.

3. A synthetic paper which comprises a film obtained by oxidizing the surface of a film obtained by stretching a resin film comprising as the base material a resin composition comprising

100 parts by weight of resin components and from 10 to 250 parts by weight of component E: fine inorganic particles;

said resin components comprising, based on the total weight of the resin components,

55-90 wt% of component A: a polypropylene resin, [55-90 wt%]

5-40 wt% of component B: a polyetheresteramide containing aromatic rings which is derived from

component b1: a polyamide having a number-average molecular weight of from 200 to 5,000 and containing a carboxyl group at each end, and

component b2: an [alkaline] alkylene oxide adduct of bisphenol having a number-average molecular weight of from 300 to 5,000, [5-40 wt%]

3-20 wt% of component C: a polyamide resin, [3-20 wt%] and

1-20 wt% of component D: at least one modified low-molecular weight polypropylene selected from the group consisting of [following components d1 to d3  
1-20 wt%]

component d1: an acid-modified low-molecular weight polypropylene having a number-average molecular weight of from 800 to 25,000 and an acid value of from 5 to 150,

component d2: a hydroxy-modified low-molecular weight polypropylene having a number-average molecular weight of from 800 to 25,000 and a hydroxyl value of from 5 to 150, and

component d3: an ester-modified low-molecular weight polypropylene obtained by partly or wholly esterifying component d1 with a polyoxyalkylene compound and having a number-average molecular weight of from 1,000 to 28,000; [,]

[The total amount of all resin components being 100 wt%, and from 10 to 250 parts by weight of component E: Fine inorganic particles,]

said stretching being conducted at a temperature lower than the melting point of the polypropylene resin as component A, wherein the stretched resin film has a void content of from 10 to 60% as calculated using the following equation (1): [ of from 10 to 60%]

$$\text{Void content (\%)} = (p^{\circ} - p) \times 100 / p^{\circ} \quad (1)$$

wherein  $p^{\circ}$  [:] is a density of the unstretched film, and

$p$  [:] is a density of the stretched film.